

Assan PU SEALANT 40 SHORE A



Product Description

AssanPU Sealant is a single-component, moisture curing, polyurethane-based sealant bonding material.

Properties

- One-component.
- Easy application with gun.
- Thixotropic.
- Cures with the humidity in the air.
- Paintable
- No volume change.
- Resistant to weather conditions and water.
- Permanent elasticity.
- No over joint expansion-bubble free curing

Technical Information

| | |
|----------------------------|---|
| Chemical Base | Polyurethane |
| Curing Mechanism | Atmospheric Moisture |
| Specific gravity | 1,15 ± 0,03 g/cm ³ (DIN 53479) |
| Tack free time | 60-90 min. (25°C ve 50% bağıl nem) |
| Cure Rate | 2 mm/24 hour (25°C ve 50% bağıl nem) |
| Hardness (shore A) | 40±5 Shore A (ASTM D 53505) |
| Elongation at Break | ≥%500 (DIN 53504) |
| Modulus 100 % | >0,4 Mpa (DIN 53504) |
| Tensile Strength | 10 N/mm |

Application Details

| | |
|--------------------------------|------------------|
| Application Temperature | +5 °C to +35 °C |
| Temperature Resistance | -30 °C to +80 °C |

The application surface must be solid, clean, dry and free of dust, oil and grease. Apply a primer if necessary. If necessary, rub down metal surfaces before usage. Allow the substrate to dry after degreasing. It is recommended to clean concrete with a metal brush.

Assan PU Sealant;

- Is capable of adhesion to cement-based building materials, brick, ceramic, marble, glass, wood, galvanize steel, aluminum and most plastic surfaces.
- Used in construction industry, in the cavities of the joints between building elements
- Used for joints and assembly of aluminum, PVC, wooden framing
- Used for laying of roof tiles

Usage

- Can be applied by a manual or pneumatic gun.
- After application, it is needed to smooth the joint with soapy water.
- It is suggested to use cartridge or sausage in 24 hours after opening .
- Do not apply at a temperature under 5 °C.
- In cold weather, store the packages at about 20 °C before use.
- Can not be used on bituminous substrates, natural rubber, EPDM rubber or on building materials which might bleed oils, plasticizers or solvents which could attack the sealant.
- If there is a moisture-vapor-transmission condition exists from the substrate as this can cause bubbling within the sealant.
- Opened cartridges should be used the same day.
- During application, avoid air-entrapment
- There can be slightly color change in white and grey shades when exposed to ultraviolet rays. Does not affect your product performance
- Avoid contact with alcohol and solvent cleaners during cure.
- Maximum depth of sealant must not exceed 12 mm; minimum depth is 0,5 mm.

Cleaning

Tools can be cleaned with alcohol or acetone before the sealant has completely cured. After curing, abrasion is necessary.

Chemical Resistance

Resistant to water, seawater, diluted alkalis, cement grout and water dispersed detergent. Not resistant to alcohols, organic acids, concentrated alkalis and concentrated acids, chlorinated (hydro-carbons) fuel.

Packaging

In 600 ml aluminum sausage,
in 280 ml aluminum cartridge

Colors

White/Black/Red/Grey/Anthracite
aluminum sausage and aluminum cartridge with option.

Shelf Life

Store the product in a cool and dry place.
The shelf life is 12 months at temperatures between +5°C and +25°C.

Caution

Keep out of reach of children.
Avoid contact with skin and eyes.
Use in well-ventilated places.
Don't breathe vapors.
Do not smoke when using the product.

Health and Safety

For more information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing, physical, ecological, and toxicological and other safety related data.